




Europäisches  
Patentamt

European  
Patent Office

Office européen  
des brevets



Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-  
gen stimmen mit der  
ursprünglich eingereichten  
Fassung der auf dem näch-  
sten Blatt bezeichneten  
europäischen Patentanmel-  
dung überein.

The attached documents  
are exact copies of the  
European patent application  
described on the following  
page, as originally filed.

Les documents fixés à  
cette attestation sont  
conformes à la version  
initialement déposée de  
la demande de brevet  
européen spécifiée à la  
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

03102024.1

**PRIORITY  
DOCUMENT**  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts;  
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets  
p.o.

R C van Dijk

Europäisches  
PatentamtEuropean  
Patent OfficeOffice européen  
des brevets

Anmeldung Nr:  
Application no.: 03102024.1  
Demande no:

Anmeldetag:  
Date of filing: 04.07.03  
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

ATOFINA Research  
Zone Industrielle C  
7181 Seneffe (Feluy)  
BELGIQUE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:  
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.  
If no title is shown please refer to the description.  
Si aucun titre n'est indiqué se referer à la description.)

Polymerisation process

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)  
revendiquée(s)  
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/  
Classification internationale des brevets:

C08F212/00

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of  
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL  
PT RO SE SI SK TR LI

## POLYMERISATION PROCESS

The present invention relates to a process for the production of a co-polymer, in particular a co-polymer comprising styrene units and units of another olefin monomer. The co-polymer produced according to the present method is generally a random co-polymer which is crystalline and easily processible.

In the past, attempts have been made to produce random olefin polymers using metallocene catalysts. In *Angew. Chem. Int. Ed.* 1998, Vol. 37, No. 7, pages 922-925, Leclerc and Waymouth describe metallocene compounds having a cyclopentadiene ligand (Cp) and a fluorene ligand (Flu), which can be used in the co-polymerisation of ethene and propylene. In particular, zirconium metallocene catalysts comprising unsubstituted Cp, 3-methyl Cp, 3-*tert*-butyl Cp and 3,4-dimethyl Cp ligands are disclosed. These catalysts are only partially successful in producing random polymers, and a significant degree of randomisation always remains in polymer products produced using these catalysts.

Metallocene catalysts are known to be useful in various polymerisation processes. For example, in EP 0581236, specific metallocene catalysts are described as being useful for the production of isotactic polypropylene (iPP).

However, up to present methods for producing olefin-styrene co-polymers are not entirely satisfactory, particularly in slurry processes. This is due to the nature of styrene, which is difficult to polymerise in this way. Styrene is very reactive, when compared with most other commonly used monomers (such as ethylene and propylene) and tends to polymerise with itself before any co-monomer can be incorporated into the polymer. Thus, previous attempts to produce styrene co-polymers have succeeded only in producing mixtures of polystyrene with another polymer, or polystyrene with a very small co-monomer content. There is thus still a need for an improved method of forming olefin-styrene co-polymers, especially random olefin styrene polymers where the styrene

and its co-monomer are incorporated randomly (or quasi-randomly, such as in an alternating fashion) throughout the co-polymer.

A further problem is that known random polymers have retained a large amount of solubles (extractables). These are low molecular weight highly co-polymerised species. This was a problem with the use of first generation catalysts, such as chromium and Ziegler-Natta catalysts. The solubles migrate to the surface creating a haze in the films, which is a disadvantage for many uses particularly in the food and medical areas.

With a view to overcoming these problems, attempts were made to replace these catalysts with bis-indenyl metallocene catalysts. This led to much more homogeneous chain compositions. However, it proved difficult and expensive to produce pure racemic bis-indenyl catalysts, and even when this can be achieved, the pure catalysts unavoidably undergo some conversion to their meso derivatives. The meso derivative produces atactic polyolefins which are generally soluble/extractable as discussed above.


Accordingly, it is an object of the present invention to solve the problems associated with the above prior art. It is a further object of the present invention to provide an improved method for the formation of olefin-styrene co-polymers, especially random and quasi-random co-polymers, which polymers have improved properties, such as good crystallinity and easy processability. It is also an object of the invention to produce olefin-styrene co-polymers having good clarity and transparency characteristics, and a low solubles content. It is a further object of the present invention to provide an improved method for forming olefin-styrene co-polymers having such improved properties.

Thus, the present invention provides a method for the production of a co-polymer of styrene and a further olefin monomer, which method comprises co-polymerising styrene and the further monomer in the presence of a metallocene catalyst, wherein the metallocene catalyst comprises a metallocene having the following formula (I):



wherein Cp comprises a cyclopentadienyl ring; Flu comprises a fluorenyl ring; R'' comprises a structural bridge imparting stereorigidity to the component; each R is the same or different and is an organic group; m is an integer of from 0-4; each R' is the same or different and is an organic group; n is an integer of from 0-8; M is a metal atom from group IVB of the Periodic Table or is vanadium; and each Q is a hydrocarbon having from 1-20 carbon atoms or is a halogen;

or the formula (II):



wherein Flu is a substituted or unsubstituted fluorenyl ring; R'' is a structural bridge between Flu and X imparting stereorigidity to the component; each R is the same or different and is selected from a hydrocarbyl group having from 1-20 carbon atoms, a halogen, an alkoxy group, an alkoxyalkyl group, an alkylamino group or an alkylsilylo group; q is an integer from 0-8; X is a heteroatom from group VA or group VIA; M is a metal atom from group IIIB, IVB, VB or VIB in any of its theoretical oxidation states; and each Q is a hydrocarbon having from 1-20 carbon atoms or is a halogen; p is an integer which is the oxidation state of M minus 2; and wherein the FluR<sub>q</sub> group is preferably symmetrically substituted.

The methods of the present invention involve a process of co-polymerisation. In the context of the present invention, co-polymerisation means polymerising two or more olefin monomers, one of which being a styrene monomer, together in the same reaction zone under polymerisation conditions. It is preferred that the present method involves the co-polymerisation of styrene with one further olefin monomer to form an olefin-styrene co-polymer. However, two, three or more further olefin monomers may be polymerised together with styrene in the present methods, if desired, to form, for example, a terpolymer.

The methods of the present invention are particularly advantageous, since they allow for the production of improved styrene-olefin co-polymers, especially random co-polymers, having good processibility, and high crystallinity and good optical properties, such as low haze and high transparency. The catalysts used in the present invention have no meso form (they are single site catalysts) and do not suffer the problems of producing extractables, or low molecular weight product.

The present invention will now be described in further detail, by way of example only, with reference to the following Figure, in which:

Figure 1 shows a  $^{13}\text{C}$  NMR spectrum of a styrene-propylene co-polymer, produced using  $\text{Me}_2\text{Si}(3,6\text{-}^t\text{Bu fluorenyl})(^t\text{BuN}) \text{TiCl}_2$  showing the co-polymeric nature of the product and the relative proportion of each monomer incorporated in the product.

The substituents that may be present on the cyclopentadiene and fluorene rings (R and R' respectively) will now be described in more detail. The substituent or substituents are not particularly limited. The cyclopentadiene ring (Cp) may be unsubstituted, but is preferably at least mono-substituted. If desired, it may comprise one or more further substituents, provided that these further substituents do not adversely interfere with the ability of the present method to produce random olefin co-polymers. The Cp ring may be substituted with the same substituent throughout, or with different substituents. The fluorene ring (Flu) may be substituted or unsubstituted and may also be substituted with the same substituent throughout, or with different substituents.

The substituents on the Cp and Flu rings are not particularly limited and may comprise any organic group and/or one or more atoms from any of groups IIIA, IVA, VA, VIA or VIIA of the Periodic Table, such as a B, Si, N, P, O, or S atom or a halogen atom (e.g. F, Cl, Br or I).

When the substituent comprises an organic group, the organic group preferably comprises a hydrocarbon group. The hydrocarbon group may comprise a straight chain, a branched chain or a cyclic group. Independently, the hydrocarbon group may comprise an aliphatic or an aromatic group. Also independently, the hydrocarbon group may comprise a saturated or unsaturated group.

When the hydrocarbon comprises an unsaturated group, it may comprise one or more alkene functionalities and/or one or more alkyne functionalities. When the hydrocarbon comprises a straight or branched chain group, it may comprise one or more primary, secondary and/or tertiary alkyl groups. When the hydrocarbon comprises a cyclic group it may comprise an aromatic ring, an aliphatic ring, a heterocyclic group, and/or fused ring derivatives of these groups. The cyclic group may thus comprise a benzene, naphthalene, anthracene, indene, fluorene, pyridine, quinoline, thiophene, benzothiophene, furan, benzofuran, pyrrole, indole, imidazole, thiazole, and/or an oxazole group, as well as regioisomers of the above groups.

The number of carbon atoms in the hydrocarbon group is not especially limited, but preferably the hydrocarbon group comprises from 1-40 C atoms. The hydrocarbon group may thus be a lower hydrocarbon (1-6 C atoms) or a higher hydrocarbon (7 C atoms or more, e.g. 7-40 C atoms). The number of atoms in the ring of the cyclic group is not especially limited, but preferably the ring of the cyclic group comprises from 3-10 atoms, such as 3, 4, 5, 6 or 7 atoms.

The groups comprising heteroatoms described above, as well as any of the other groups defined above, may comprise one or more heteroatoms from any of groups IIIA, IVA, VA, VIA or VIIA of the Periodic Table, such as a B, Si, N, P, O, or S atom or a halogen atom (e.g. F, Cl, Br or I). Thus the substituent may comprise one or more of any of the common functional groups in organic chemistry, such as hydroxy groups, carboxylic acid groups, ester groups, ether groups, aldehyde groups, ketone groups, amine groups, amide groups, imine groups, thiol groups, thioether groups, sulphate groups, sulphonic acid

groups, and phosphate groups etc. The substituent may also comprise derivatives of these groups, such as carboxylic acid anhydrides and carboxylic acid halides.

In addition, any substituent may comprise a combination of two or more of the substituents and/or functional groups defined above.

Typically, the substituents are independently selected from an aryl group and a hydrocarbyl group having from 1-20 carbon atoms. The most preferred substituents are methyl groups. Other preferred substituents include Et, n-Pr, i-Pr, n-Bu, t-Bu, Me<sub>3</sub>Si, R-O, cycloalkyl, and halogen.

In respect of the Cp ring, it is especially preferred that at least one group R comprises a bulky group of the formula ZR\*<sub>3</sub> in which Z is an atom from group IVA of the Periodic Table and each R\* is the same or different and is chosen from a hydrogen or a hydrocarbyl group having from 1-20 carbon atoms. When such an R group is present, it is also preferred that at least one further group R is present comprising a group of the formula YR#<sub>3</sub> in which Y is an atom from group IVA of the Periodic Table, and each R# is the same or different and is chosen from a hydrogen or a hydrocarbyl group having from 1-7 carbon atoms.

Regarding the position of the substituents, generally at least one group R is positioned on the cyclopentadienyl ring such that it is distal to the bridge R". However, in some embodiments of the invention at least one group R is positioned on the cyclopentadienyl ring such that it is proximal to the bridge R". It is particularly preferable that the cyclopentadienyl ring comprises a bulky substituent ZR\*<sub>3</sub> distal to the bridge R" and a substituent YR#<sub>3</sub> proximal to the bridge and non-vicinal to ZR\*<sub>3</sub>. In some embodiments of the present invention, the cyclopentadienyl ring comprises a substituent ZR\*<sub>3</sub> distal to the bridge R"; a substituent YR#<sub>3</sub> proximal to the bridge R" and non-vicinal to ZR\*<sub>3</sub>; and a further substituent YR#<sub>3</sub> proximal to the bridge and vicinal to ZR\*<sub>3</sub>. The


cyclopentadienyl ring may also comprise two substituents  $ZR^*_3$ , each distal to the bridge  $R''$ , if desired.

In a preferred embodiment, Z and Y in the above formulae independently comprise carbon or silicon. The catalyst compounds used in the present method are typically compounds in which  $ZR^*_3$  is selected from  $C(CH_3)_3$ ,  $C(CH_3)_2Ph$ ,  $CPh_3$ , and  $Si(CH_3)_3$ . It is particularly preferred that  $ZR^*_3$  comprises  $C(CH_3)_3$ . In further preferred embodiments of the present invention,  $YR^*_3$  comprises a methyl group or a trimethylsilyl group (TMS)

The substitution pattern of the fluorene ring (on both types of catalyst I and II) is not especially limited, provided that it does not adversely interfere with the co-polymerisation method of the present invention. The fluorene ring generally comprises a substituent at the 3-position or at the 6-position. Most preferably both the 3- and the 6-position are substituted in catalysts of type (I), and of type (II). Alternatively the fluorene ring comprises a substituent at the 2-position and/or at the 7-position. Most preferably both the 2- and the 7-position are substituted in catalysts of both types (I) and (II).

In respect of catalysts of type (II), it is preferred that the group X is an atom from group VA of the periodic table, particularly N or P. When X is from group VIA it will be apparent that X is not further substituted. However, when X is from group VA, it will be apparent that X will be further substituted to make up the required valence of the N or P atom. In this instance, further substitution may be any hydrocarbon group already discussed above. Most preferably however, the group is a bulky group, such as a tertiary butyl group.

The catalysts of type (II) most preferably have the following structure:



wherein  $R^1$  and  $R^2$  are substituents at both the 2- and 7-positions, or both the 3- and 6-positions of the fluorenyl group, and are bulky groups of the formula  $ZR^*_3$  in which Z is an atom from group IVA of the Periodic Table and each  $R^*$  is the same or different and is chosen from a hydrogen or a hydrocarbyl group having from 1-20 carbon atoms.

In the more preferred embodiments,  $R^1$  and  $R^2$  are both  $tBu$  groups. It is particularly preferred that these  $tBu$  groups are in the 3-position and the 6-position.

The type of bridge present between the rings in the above-described catalysts is not itself particularly limited. Typically  $R''$  comprises an alkylidene group having 1 to 20 carbon atoms, a germanium group (e.g. a dialkyl germanium group), a silicon group (e.g. a dialkyl silicon group), a siloxane group (e.g. a dialkyl siloxane group), an alkyl phosphine group or an amine group. Preferably, the substituent comprises a silyl radical or a hydrocarbyl radical having at least one carbon atom to form the bridge, such as a substituted or unsubstituted ethylenyl radical (e.g.  $-CH_2CH_2-$ ). Most preferably  $R''$  is isopropylidene ( $Me_2C$ ),  $Ph_2C$ , ethylenyl, or  $Me_2Si$ .


It is further preferred that the metallocene compounds used in the present invention are those wherein M is Ti, Zr, or Hf. Typically, the Q groups attached to the metal atoms are halogen atoms, such as Cl.

The further olefin employed in the present invention is not particularly limited, and may be any olefin. Suitable olefins include ethylene, propylene, butene, pentene and hexene. Preferably the olefin is an  $\alpha$ -olefin. It is also preferred that the olefin has 3 or more carbon atoms. The most preferable olefin is propylene.


In addition to the above metallocene compound, the catalyst used in the present methods may comprise one or more activating agents capable of activating any one or more of the catalyst components. Typically, the activating agent comprises an aluminium- or boron-containing activating agent.

Suitable aluminium-containing activating agents comprise an alumoxane, an alkyl aluminium compound and/or a Lewis acid.

The alumoxanes that can be used in the present invention are well known and preferably comprise oligomeric linear and/or cyclic alkyl alumoxanes represented by the formula (I):




for oligomeric linear alumoxanes; and formula (II)




for oligomeric cyclic alumoxanes,

wherein n is 1-40, preferably 10-20; m is 3-40, preferably 3-20; and R is a C<sub>1</sub>-C<sub>8</sub> alkyl group, preferably methyl. Generally, in the preparation of alumoxanes from, for example, aluminium trimethyl and water, a mixture of linear and cyclic compounds is obtained.

Suitable boron-containing activating agents may comprise a triphenylcarbenium boronate, such as tetrakis-pentafluorophenyl-borato-triphenylcarbenium as described in EP-A-0427696:



or those of the general formula below, as described in EP-A-0277004 (page 6, line 30 to page 7, line 7):



Other preferred activating agents include hydroxy isobutylaluminium and a metal aluminoxinate. These are particularly preferred when at least one Q in the general formula for metallocenes comprises an alkyl group.

The catalyst systems employed in the present invention may be employed in any type of co-polymerisation method, provided that the required catalytic activity is not impaired. In a preferred embodiment of the present invention, the catalyst system is employed in a solution polymerisation process, which is homogeneous, or a slurry process, which is heterogeneous. In a solution process, typical solvents include hydrocarbons having 4-7

carbon atoms such as heptane, toluene or cyclohexane. In a slurry process, it is necessary to immobilise the catalyst system on an inert support, particularly a porous solid support such as talc, inorganic oxides and resinous support materials such as polyolefin. Preferably, the support material is an inorganic oxide in its finely divided form.

Suitable inorganic oxide materials that are desirably employed in accordance with this invention include group IIA, IIIA, IVA, or IVB metal oxides such as silica, alumina and mixtures thereof. Other inorganic oxides that may be employed, either alone or in combination with the silica or alumina, are magnesia, titania, zirconia, and the like. Other suitable support materials, however, can be employed, for example, finely divided functionalised polyolefins such as finely divided polyethylene.

Preferably, the support is a silica support having a surface area of from 200-700 m<sup>2</sup>/g and a pore volume of from 0.5-3 ml/g.

The amount of activating agent and metallocene usefully employed in the preparation of the solid support catalyst can vary over a wide range. Preferably, the activating agent to transition metal mole ratio is in the range between 1:1 and 100:1, preferably in the range 5:1 and 50:1.

The order of addition of the catalyst components and activating agent to the support material can vary. In accordance with a preferred embodiment of the present invention activating agent dissolved in a suitable inert hydrocarbon solvent is added to the support material slurried in the same or other suitable hydrocarbon liquid and thereafter a mixture of the catalyst components is added to the slurry.

Preferred solvents include mineral oils and the various hydrocarbons which are liquid at reaction temperature and which do not react with the individual ingredients. Illustrative examples of the useful solvents include the alkanes such as pentane, iso-pentane, hexane, heptane, octane and nonane; cycloalkanes such as cyclopentane and cyclohexane, and aromatics such as benzene, toluene, ethylbenzene and diethylbenzene.


Preferably, the support material is slurried in toluene and the catalyst components and activating agent are dissolved in toluene prior to addition to the support material.

The present invention further provides use of a metallocene catalyst for producing a co-polymer of styrene and a further olefin monomer, wherein the metallocene catalyst comprises a metallocene having the following formula (I):



wherein Cp comprises a cyclopentadienyl ring; Flu comprises a fluorenyl ring; R'' comprises a structural bridge imparting stereorigidity to the component; each R is the same or different and is an organic group; m is an integer of from 0-4; each R' is the same or different and is an organic group; n is an integer of from 0-8; M is a metal atom from group IVB of the Periodic Table or is vanadium; and each Q is a hydrocarbon having from 1-20 carbon atoms or is a halogen;

or the formula (II):



wherein Flu is a substituted or unsubstituted fluorenyl ring; R'' is a structural bridge between Flu and X imparting stereorigidity to the component; each R is the same or different and is selected from a hydrocarbyl group having from 1-20 carbon atoms, a halogen, an alkoxy group, an alkoxyalkyl group, an alkylamino group or an alkylsilylo group; q is an integer from 0-8; X is a heteroatom from group VA or group VIA; M is a metal atom from group IIIB, IVB, VB or VIB in any of its theoretical oxidation states; and each Q is a hydrocarbon having from 1-20 carbon atoms or is a halogen; and wherein the FluR<sub>q</sub> group is preferably symmetrically substituted.


Also provided is a co-polymer, obtainable according to the methods defined above. The co-polymer is preferably a styrene-propylene co-polymer in which there is reasonably even distribution of the styrene and propylene units throughout each polymer molecule so that large blocks of each monomer unit do not form. Without being bound by theory, it is thought that this provides the polymer with its advantageous crystallinity, optical properties and processibility.

Applications for which the polymers of the present invention are particularly suited include films and impact co-polymers.

The present invention will now be described in further detail, by way of example only, with reference to the following specific embodiments.

### Example

In order to demonstrate the utility of the catalysts and methods of the present invention, a styrene-propylene co-polymer was produced in a standard polymerisation procedure, using  $\text{Me}_2\text{Si}(3,6\text{-}^t\text{Bu fluorenyl})(^t\text{BuN})\text{TiCl}_2$ :



The final polymer proved to be a genuine co-polymer of propylene and styrene, comprising approximately 10 % (from 9-11%) styrene by weight. Such polymers could not be produced in the past.

The composition of the co-polymer was confirmed by  $^1\text{H}$  and  $^{13}\text{C}$  NMR spectroscopy. The  $^{13}\text{C}$  NMR spectrum for the product is depicted in Figure 1, showing the co-polymeric nature of the product and the relative proportion of each monomer incorporated in the product.


## CLAIMS:

1. A method for the production of a co-polymer of styrene and a further olefin monomer, which method comprises co-polymerising styrene and the further monomer in the presence of a metallocene catalyst, wherein the metallocene catalyst comprises a metallocene having the following formula (I):



wherein Cp comprises a cyclopentadienyl ring; Flu comprises a fluorenyl ring; R'' comprises a structural bridge imparting stereoridity to the component; each R is the same or different and is an organic group; m is an integer of from 0-4; each R' is the same or different and is an organic group; n is an integer of from 0-8; M is a metal atom from group IVB of the Periodic Table or is vanadium; and each Q is a hydrocarbon having from 1-20 carbon atoms or is a halogen;

or the formula (II):




wherein Flu is a substituted or unsubstituted fluorenyl ring; R'' is a structural bridge between Flu and X imparting stereoridity to the component; each R is the same or different and is selected from a hydrocarbyl group having from 1-20 carbon atoms, a halogen, an alkoxy group, an alkoxyalkyl group, an alkylamino group or an alkylsilylo group; q is an integer from 0-8; X is a heteroatom from group VA or group VIA; M is a metal atom from group IIIB, IVB, VB or VIB in any of its theoretical oxidation states; and each Q is a hydrocarbon having from 1-20 carbon atoms or is a halogen; p is an integer which is the oxidation state of M minus 2; and wherein the FluR<sub>q</sub> group is preferably symmetrically substituted.

2. A method according to claim 1, wherein at least one group R in formula (I) is positioned on the cyclopentadienyl such that it is distal to the bridge R", which group R comprises a bulky group of the formula  $ZR^*_3$  in which Z is an atom from group IVA of the Periodic Table and each  $R^*$  is the same or different and is chosen from a hydrogen or a hydrocarbyl group having from 1-20 carbon atoms.
3. A method according to claim 2, wherein the cyclopentadienyl ring of formula (I) comprises a substituent  $ZR^*_3$  distal to the bridge R" and a substituent  $YR^{\#}_3$  proximal to the bridge and non-vicinal to  $ZR^*_3$ , wherein Y is an atom from group IVA of the Periodic Table, and each  $R^{\#}$  is the same or different and is chosen from a hydrogen or a hydrocarbyl group having from 1-7 carbon atoms.
4. A method according to claim 2 or claim 3, wherein Z and/or Y comprises carbon or silicon.
5. A method according to claim 4, wherein  $ZR^*_3$  comprises  $C(CH_3)_3$  and/or  $YR^{\#}_3$  comprises  $CH_3$ .
6. A method according to claim 1, wherein X in formula (II) is N or P.
7. A method according to any preceding claim, wherein the fluorine ring in formula (I) or formula (II) comprises a substituent at the 3-position and/or at the 6-position, or a substituent at the 2-position and/or at the 7-position.
8. A method according to any preceding claim, wherein R" comprises an alkylidene group having 1 to 20 carbon atoms, a germanium group, a silicon group, a siloxane group, an alkyl phosphine group, or an amine group.

9. A method according to claim 8, wherein R" comprises a substituted or unsubstituted ethylenyl group, an isopropylidene (Me<sub>2</sub>C) group, a Ph<sub>2</sub>C group, or a Me<sub>2</sub>Si group.

10. A method according to any preceding claim, wherein M is Ti, Zr, or Hf.

11. A method according to any preceding claim, wherein the catalyst has the following structure:



wherein R<sup>1</sup> and R<sup>2</sup> are substituents at both the 2- and 7-positions, or both the 3- and 6-positions of the fluorenyl group, and are bulky groups of the formula ZR\*<sub>3</sub> in which Z is an atom from group IVA of the Periodic Table and each R\* is the same or different and is chosen from a hydrogen or a hydrocarbyl group having from 1-20 carbon atoms.

12. A method according to claim 11, wherein R<sup>1</sup> and R<sup>2</sup> are both <sup>t</sup>Bu groups.


13. A method according to any preceding claim, wherein the further olefin monomer is propylene.

14. Use of a metallocene catalyst for producing a co-polymer of styrene and a further olefin monomer, wherein the metallocene catalyst comprises a metallocene having the following formula (I):



wherein Cp comprises a cyclopentadienyl ring; Flu comprises a fluorenyl ring; R'' comprises a structural bridge imparting stereorigidity to the component; each R is the same or different and is an organic group; m is an integer of from 0-4; each R' is the same or different and is an organic group; n is an integer of from 0-8; M is a metal atom from group IVB of the Periodic Table or is vanadium; and each Q is a hydrocarbon having from 1-20 carbon atoms or is a halogen;

or the formula (II):



wherein Flu is a substituted or unsubstituted fluorenyl ring; R'' is a structural bridge between Flu and X imparting stereorigidity to the component; each R is the same or different and is selected from a hydrocarbyl group having from 1-20 carbon atoms, a halogen, an alkoxy group, an alkoxyalkyl group, an alkylamino group or an alkylsilylo group; q is an integer from 0-8; X is a heteroatom from group VA or group VIA; M is a metal atom from group IIIB, IVB, VB or VIB in any of its theoretical oxidation states; and each Q is a hydrocarbon having from 1-20 carbon atoms or is a halogen; p is an integer which is the oxidation state of M minus 2; and wherein the FluR<sub>q</sub> group is preferably symmetrically substituted.

15. Use according to claim 14, wherein the metallocene compound is a compound as defined in any of claims 2-12.

16. Use according to claim 14 or claim 15, wherein the further olefin monomer is propylene.

17. A co-polymer, formed from styrene and a further olefin monomer, obtainable according to a method as defined in any of claims 1-13.

18. A co-polymer according to claim 17, which co-polymer is a substantially random co-polymer, or a block co-polymer.


19. A co-polymer according to claim 17 or claim 18, which co-polymer comprises from 5-50 wt.% of styrene.

20. A co-polymer according to any of claims 17-19, wherein the further olefin monomer is propylene.

## ABSTRACT


## POLYMERISATION PROCESS

Provided is a method for the production of a co-polymer of styrene and a further olefin monomer, which method comprises co-polymerising styrene and the further monomer in the presence of a metallocene catalyst, wherein the metallocene catalyst comprises a metallocene having the following formula (I):




wherein Cp comprises a cyclopentadienyl ring; Flu comprises a fluorenyl ring; R'' comprises a structural bridge imparting stereorigidity to the component; each R is the same or different and is an organic group; m is an integer of from 0-4; each R' is the same or different and is an organic group; n is an integer of from 0-8; M is a metal atom from group IVB of the Periodic Table or is vanadium; and each Q is a hydrocarbon having from 1-20 carbon atoms or is a halogen;

or the formula (II):



wherein Flu is a substituted or unsubstituted fluorenyl ring; R'' is a structural bridge between Flu and X imparting stereorigidity to the component; each R is the same or different and is selected from a hydrocarbyl group having from 1-20 carbon atoms, a halogen, an alkoxy group, an alkoxyalkyl group, an alkylamino group or an alkylsilylo group; q is an integer from 0-8; X is a heteroatom from group VA or group VIA; M is a metal atom from group IIIB, IVB, VB or VIB in any of its theoretical oxidation states; and each Q is a hydrocarbon having from 1-20 carbon atoms or is a halogen; p is an integer which is the oxidation state of M minus 2; and wherein the FluR<sub>q</sub> group is preferably symmetrically substituted.

FIGURE 1



PCT/EP2004/051262



# PATENT COOPERATION TREATY

# PCT

## INTERNATIONAL PRELIMINARY REPORT ON PATENTABILITY

(Chapter I of the Patent Cooperation Treaty)

(PCT Rule 44bis)

Applicant's or agent's file reference F-875 WO	<b>FOR FURTHER ACTION</b>	See item 4 below
International application No. PCT/EP2004/051262	International filing date ( <i>day/month/year</i> ) 28 June 2004 (28.06.2004)	Priority date ( <i>day/month/year</i> ) 04 July 2003 (04.07.2003)
International Patent Classification (8th edition unless older edition indicated) See relevant information in Form PCT/ISA/237		
Applicant TOTAL PETROCHEMICALS RESEARCH FELUY		

1. This international preliminary report on patentability (Chapter I) is issued by the International Bureau on behalf of the International Searching Authority under Rule 44 *bis*.1(a).

2. This REPORT consists of a total of 8 sheets, including this cover sheet.

In the attached sheets, any reference to the written opinion of the International Searching Authority should be read as a reference to the international preliminary report on patentability (Chapter I) instead.

3. This report contains indications relating to the following items:

- |                                     |              |   |
|-------------------------------------|--------------|---|
| <input checked="" type="checkbox"/> | Box No. I    | Basis of the report   |
| <input checked="" type="checkbox"/> | Box No. II   | Priority  |
| <input type="checkbox"/>            | Box No. III  | Non-establishment of opinion with regard to novelty, inventive step and industrial applicability  |
| <input type="checkbox"/>            | Box No. IV   | Lack of unity of invention  |
| <input checked="" type="checkbox"/> | Box No. V    | Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement |
| <input type="checkbox"/>            | Box No. VI   | Certain documents cited   |
| <input checked="" type="checkbox"/> | Box No. VII  | Certain defects in the international application  |
| <input checked="" type="checkbox"/> | Box No. VIII | Certain observations on the international application   |

4. The International Bureau will communicate this report to designated Offices in accordance with Rules 44bis.3(c) and 93bis.1 but not, except where the applicant makes an express request under Article 23(2), before the expiration of 30 months from the priority date (Rule 44bis .2).

The International Bureau of WIPO 34, chemin des Colombettes 1211 Geneva 20, Switzerland  Facsimile No. +41 22 740 14 35	Date of issuance of this report 09 January 2006 (09.01.2006)  Authorized officer  <p style="text-align: center; font-weight: bold;">Agnes Wittmann-Regis</p> Telephone No. +41 22 338 89 70
---	--

# PATENT COOPERATION TREATY

From the  
INTERNATIONAL SEARCHING AUTHORITY

REC'D 19 NOV 2004

WIPO

PCT

PCT

To:

see form PCT/ISA/220

20/1

## WRITTEN OPINION OF THE INTERNATIONAL SEARCHING AUTHORITY (PCT Rule 43bis.1)

Date of mailing

(day/month/year) see form PCT/ISA/210 (second sheet)

Applicant's or agent's file reference

see form PCT/ISA/220

### FOR FURTHER ACTION

See paragraph 2 below

International application No.

PCT/EP2004/051262

International filing date (day/month/year)

28.06.2004

Priority date (day/month/year)

04.07.2003

International Patent Classification (IPC) or both national classification and IPC

C08F210/06, C08F4/642, C08F4/76

Applicant

ATOFINA RESEARCH

### 1. This opinion contains indications relating to the following items:

- ☒ Box No. I Basis of the opinion
- ☒ Box No. II Priority
- ☐ Box No. III Non-establishment of opinion with regard to novelty, inventive step and industrial applicability
- ☐ Box No. IV Lack of unity of invention
- ☒ Box No. V Reasoned statement under Rule 43bis.1(a)(i) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement
- ☐ Box No. VI Certain documents cited
- ☒ Box No. VII Certain defects in the international application
- ☒ Box No. VIII Certain observations on the international application

### 2. FURTHER ACTION

If a demand for International preliminary examination is made, this opinion will usually be considered to be a written opinion of the International Preliminary Examining Authority ("IPEA"). However, this does not apply where the applicant chooses an Authority other than this one to be the IPEA and the chosen IPEA has notified the International Bureau under Rule 66.1bis(b) that written opinions of this International Searching Authority will not be so considered.

If this opinion is, as provided above, considered to be a written opinion of the IPEA, the applicant is invited to submit to the IPEA a written reply together, where appropriate, with amendments, before the expiration of three months from the date of mailing of Form PCT/ISA/220 or before the expiration of 22 months from the priority date, whichever expires later.

For further options, see Form PCT/ISA/220.

### 3. For further details, see notes to Form PCT/ISA/220.

Name and mailing address of the ISA:



European Patent Office - P.B. 5818 Patentlaan 2  
NL-2280 HV Rijswijk - Pays Bas  
Tel. +31 70 340 - 2040 Tx: 31 651 epo nl  
Fax: +31 70 340 - 3016

Authorized Officer

Parry, J

Telephone No. +31 70 340-1032



**WRITTEN OPINION OF THE  
INTERNATIONAL SEARCHING AUTHORITY**

International application No.  
PCT/EP2004/051262

---

**Box No. I Basis of the opinion**

---

1. With regard to the **language**, this opinion has been established on the basis of the international application in the language in which it was filed, unless otherwise indicated under this item.  
☐ This opinion has been established on the basis of a translation from the original language into the following language , which is the language of a translation furnished for the purposes of international search (under Rules 12.3 and 23.1(b)).
2. With regard to any **nucleotide and/or amino acid sequence** disclosed in the international application and necessary to the claimed invention, this opinion has been established on the basis of:
  - a. type of material:  
☐ a sequence listing  
☐ table(s) related to the sequence listing
  - b. format of material:  
☐ in written format  
☐ in computer readable form
  - c. time of filing/furnishing:  
☐ contained in the international application as filed.  
☐ filed together with the international application in computer readable form.  
☐ furnished subsequently to this Authority for the purposes of search.
3. ☐ In addition, in the case that more than one version or copy of a sequence listing and/or table relating thereto has been filed or furnished, the required statements that the information in the subsequent or additional copies is identical to that in the application as filed or does not go beyond the application as filed, as appropriate, were furnished.
4. Additional comments:

**WRITTEN OPINION OF THE  
INTERNATIONAL SEARCHING AUTHORITY**

International application No.  
PCT/EP2004/051262

---

**Box No. II Priority**

---

1. ☒ The following document has not been furnished:

☒ copy of the earlier application whose priority has been claimed (Rule 43*bis*.1 and 66.7(a)).

☐ translation of the earlier application whose priority has been claimed (Rule 43*bis*.1 and 66.7(b)).

Consequently it has not been possible to consider the validity of the priority claim. This opinion has nevertheless been established on the assumption that the relevant date is the claimed priority date.

2. ☐ This opinion has been established as if no priority had been claimed due to the fact that the priority claim has been found invalid (Rules 43*bis*.1 and 64.1). Thus for the purposes of this opinion, the international filing date indicated above is considered to be the relevant date.

3. Additional observations, if necessary:

---

**Box No. V Reasoned statement under Rule 43*bis*.1(a)(i) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement**

---

1. Statement

Novelty (N)	Yes: Claims	2-4 and 6-8
	No: Claims	1,5,9-15
Inventive step (IS)	Yes: Claims	
	No: Claims	1-15
Industrial applicability (IA)	Yes: Claims	1-15
	No: Claims	

2. Citations and explanations

see separate sheet

---

**Box No. VII Certain defects in the international application**

---

The following defects in the form or contents of the international application have been noted:

see separate sheet

---

**Box No. VIII Certain observations on the international application**

---

The following observations on the clarity of the claims, description, and drawings or on the question whether the claims are fully supported by the description, are made:

see separate sheet

**Re Item V**

**Reasoned statement under Rule 66.2(a)(ii) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement**

The following documents (D1-D2, D4-D12) will be referred to (see the ISR for the relevant passages):

- D1: WO 96/07681 A (DOW CHEMICAL CO) 14 March 1996 (1996-03-14)
- D2: CAPORASO, LUCIA ET AL: "Enantioselectivity of C8- and C2-Symmetric ansa-Metallocene Catalysts in the Styrene Insertion" MACROMOLECULES (2000), 33(20), 7275-7282, 2000, XP001187513
- D4: KUO, JING-CHUNG ET AL: "Synthesis of syndiotactic polypropylene based diblock copolymer via metallocene catalyst mediated chain transfer reaction" POLYMER PREPRINTS (AMERICAN CHEMICAL SOCIETY, DIVISION OF POLYMER CHEMISTRY) (2003), 44(2), 10-11, 2003, XP008027256
- D5: DATABASE CAPLUS [Online] CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; ARAI, TOORU ET AL: "Propylene-aromatic vinyl compound copolymers with specific stereoregularity in propylene chain structure, and their efficient preparation" XP002269696 retrieved from STN Database accession no. 126:31838
- D6: DATABASE CAPLUS [Online] CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; MORI, RYOJI ET AL: "Syndiotactic propylene polymers, thermoplastic resin compositions containing them, and molded products therefrom with balanced rigidity, surface hardness, and impact resistance" XP002269697 retrieved from STN Database accession no. 133:267637
- D7: DATABASE CAPLUS [Online] CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; MICHKAMI, KENJI ET AL: "Random polymerization of aromatic vinyl monomers and olefins using aluminoxane-free metallocene catalyst systems" XP002269694 retrieved from STN Database accession no. 131:102672
- D8: DATABASE CAPLUS [Online] CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; MYATA, HIROSHI ET AL: "Ethylene-.alpha.-olefin-aromatic vinyl compound random copolymers and their manufacture" XP002269698 retrieved from STN Database accession no. 124:118309
- D9: EP-A-0 520 732 (DOW CHEMICAL CO., USA) 30 December 1992 (1992-12-30)

**WRITTEN OPINION OF THE  
INTERNATIONAL SEARCHING  
AUTHORITY (SEPARATE SHEET)**

International application No.

PCT/EP2004/051262

D10: WO 00/49029 A (FINA RESEARCH ; RAZAVI ABBAS (BE)) 24 August 2000 (2000-08-24)  
D11: EP-A-1 179 553 (ATOFINA RES) 13 February 2002 (2002-02-13)  
D12: EP-A-1 083 188 (FINA RESEARCH) 14 March 2001 (2001-03-14)

1. D1 describes compounds amongst others of the type:  $\text{Me}_2\text{C-}$  and  $\text{Me}_2\text{Si-Fluor(Cp)ZrCl}_2$ , and  $\text{Me}_2\text{Si-(Fluor-Me-4(-NtBu))TiMe}_2$  (fluor = Fluorenyl) in claim 8,  $\text{Cp}^*$  analogues of which are found in the examples. Ethylene-styrene-ethylidenenorbornene or ethylene-styrene-propylene polymers where either ethylene or styrene can be in excess are produced therewith, for example: Et(1.7 wt. %)-PP(39 wt. %)-Sty (6 wt. %). Hence claims 1, 5, and 9-15 are not novel.

2. D2 describes compounds amongst others of the type:  $\text{Me}_2\text{C-Fluor(Cp)ZrCl}_2$  which are employed in the production of ethylene-propylene-styrene polymers where propylene is in the majority, and styrene and ethylene are in equal quantities. Hence claims 1 and 9-15 are not novel.

3. D4 describes compounds amongst others of the type:  $\text{Me}_2\text{Ph-Fluor(Cp)ZrCl}_2$  which are employed in the production of propylene-styrene polymers where the styrene forms terminal groups. D4 was published in 2003 but the precise publication date is unknown. Hence claims 1, and 9-15 are not novel.

4. D5 describes catalytic systems comprising compounds of the type:  $\text{Me}_2\text{Ph-Fluor(Cp)ZrCl}_2$ ,  $\text{Me}_2\text{Ph-Fluor(Cp)ZrMe}_2$ , and  $\text{Me}_2\text{Ph-Fluor(Cp)HfCl}_2$  which yield propylene-styrene polymers with 0.5-15 mol% styrene content. Hence claims 1, and 9-15 are not novel.

5. D6 describes catalytic systems comprising compounds of the type:  $\text{Me}_2\text{Ph-Fluor(Cp)ZrCl}_2$  which yield polymers such as: ethylene(1.7 mol%)-propylene(39 mol%)-styrene(60 mol%). Hence claims 1, and 9-15 are not novel.

6. D7 describes compounds of the type  $\text{Ph}_2\text{-C-(Cp(Fluor))ZrCl}_2$  and  $\text{iPr-(Cp(Fluor))ZrCl}_2$ . Styrene(92 mol %)-propylene(8 mol %) is produced along with other polymers with the following respective amounts of monomer: 98, 2; 5, 98. Hence claims 1, and 9-15 are not novel.

7. D8 describes catalytic systems comprising compounds of the type:

Me<sub>2</sub>Ph-Fluor(Cp)ZrCl<sub>2</sub>, which yield polymers such as: ethylene-propylene(42 mol%)-styrene(0.4 mol%). Hence claims 1, and 9-14 are not novel.

8. D9 describes catalytic systems comprising compounds of the type: Me<sub>2</sub>Si-(tetrahydroFluor-))(-NtBu)TiCl<sub>2</sub> used for Ethylene-octene polymerisation. The Cp\* analogue is used for styrene(4.4 mol%)-propylene(30 mol%)-ethylene(major component) copolymerisation. Hence claims 13-15 are not novel.

9. D5 is considered to be the closest prior art because it describes, as outlined above, the production of propylene-styrene copolymers with similar constitutions to those of the present examples. The subject-matter of claims 2-4 and 6-8 differs in that certain substituents are specified at positions on cyclopentadienyl (feature 1) or fluorenyl ring (feature 2). The technical effect of these features have not been demonstrated over D5. Therefore, the objective problem can be formulated as to provide alternative catalysts for propylene-styrene copolymerisation. The solution proposed in claims 2-4 and 6-8 of the present application cannot be considered as involving an inventive step because features 1 and 2 are both disclosed in D10. D10 describes catalytic systems concerning syndiotactic polypropylene production comprising compounds of the type: Me<sub>2</sub>C-Fluor-2,6-tBu(-Cp-3-tBu-5-Me)ZrCl<sub>2</sub>. Feature 2 is also disclosed in conjunction with other ligand sets in D11 (Me<sub>2</sub>Si-Fluor-tBu-2,6(Cp)ZrCl<sub>2</sub>) and D12 (Me<sub>2</sub>Si-Fluor-tBu-2,6(-NtBu)TiCl<sub>2</sub>). The skilled person would therefore regard it as a normal option to combine the teachings of D5 with those of D10, D11 or D12 in order to solve the problem of the present application. Hence claims 2-4 and 6-8 are not inventive.

**Re Item VII**

**Certain defects in the international application**

The reference EP 0581236 on p. 1 should have read EP0881236.

**Re Item VIII**

**Certain observations on the international application**

The following objections are made under Art. 6 (PCT):

1. Claim (i) The term "co-polymer of styrene" is taken by the skilled person to mean that styrene is present in the majority, and moreover that only styrene and propylene are present in the product. However, from the description, it is clear that the amount of styrene only ranges from 2-50 wt.% (p.13) and other monomers can be present (p.3)
- (ii) the term "structural bridge imparting stereorigidity" attempts to define the invention

in terms of a "result to be achieved", which is inadmissible.

(iii) "m (or n) is...from 0-4": if m (or n) is less than 4 (or 8) then the valency of carbon in the ring structure is violated as no hydrogen atoms have been defined here.

2. Claim 2: "bulky" is meaningless as it has not been defined with respect to a point of reference. Likewise claim 11.

3. Claim 3: the scope of protection sought would have been more readily apparent if the disposition of the substituents had been defined with respect to a numbering scheme (see also point 4(ii) below).

4. Claim 7: (i) "symmetrically substituted" with respect to what plane or point?: should it have been taken to mean a reflection with respect to an (as yet) undefined plane of symmetry, or a rotation, or a reflection-rotation, or an inversion etc?  
(ii) the "positions" have not been clearly defined with respect to a numbering scheme. Likewise claim 8.

5. Claims 11 and 12: these "use" claims amount to process claims and therefore appear redundant in the light of the preceding claims.

6. Claims 13-15 are claims for a product obtained by a process. It cannot be ascertained in the final product that this material had been produced in this way.

7. Claim 14: the term "substantially" is vague.